

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification 6:</b> <b>B01J 2/02, 2/00, B05B 5/08, B01J 14/00, 19/08</b>	<b>AI</b>	<b>(11) International Publication Number:</b> <b>WO 97/49484</b> <b>(43) International Publication Date:</b> 31 December 1997 (31.12.97)
<b>(21) International Application Number:</b> PCT/NL97/00366 <b>(22) International Filing Date:</b> 27 June 1997 (27.06.97)  <b>(30) Priority Data:</b> 1003442 27 June 1996 (27.06.96) NL  <b>(71) Applicant (for all designated States except US):</b> TECHNISCHE UNIVERSITEIT DELFT [NL/NL]; Julianalaan 134, NL-2628 BL Delft (NL).  <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> BORRA, Jean-Pascal, Dominique, Maurice [FR/NL]; Franklinstraat 137, NL-2562 CC Den Haag (NL).  <b>(74) Agent:</b> ALTENBURG, Bernardus, Stephanus, Franciscus; Octrooibureau Los en Stijger B.V., Weteringschans 96, NL-1017 XS Amsterdam (NL).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> METHOD OF MANUFACTURING A DRY POWDER PARTICLE, A POWDER PRODUCED WITH SAID METHOD, AND AN ELECTRODE AND AN APPARATUS FOR USE IN SAID METHOD		
<b>(57) Abstract</b> <p>The invention relates to a method of manufacturing a dry powder particle, preferably using electrohydrodynamic spraying, wherein two oppositely charged aerosol streams are contacted. The invention allows for the manufacture of powders having various, controllable compositions and shapes. In particular the method according to the invention may be used to perform physical and chemical reactions and allows for the manufacture of powders not previously obtainable. In addition, the invention also relates to an electrode (4, 4', 5, 10a, 10b) and an apparatus for applying the method according to the invention.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LJ	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

Method of manufacturing a dry powder particle, a powder produced with said method, and an electrode and an apparatus for use in said method

This invention relates to a method of manufacturing a dry powder particle by generating a charged aerosol stream comprised of charged initially liquid particles and converting said stream into powder particles.

5           Such a method is well known in the state of the art. By passing a liquid, comprising a solute dissolved in a solvent, through a narrow orifice using high voltage, a charged aerosol stream is generated comprised of charged liquid particles. Evaporation of the solvent results in a  
10 fine powder with a relatively narrow size distribution. This process, known as electrohydrodynamic spraying, is for example suitable for the manufacture of polymeric powders used for electrostatic spraying during powder coating.

          The objects of the present invention are to expand  
15 the application possibilities of said method, and in particular to provide a method allowing for the manufacture of powders which could not be produced so far, and to improve the quality of powders produced using said method. In this application the term "manufacturing a powder" includes the  
20 manufacture of powder mixtures.

          To this end the method according to the invention is characterized in that the charged aerosol stream comprised of charged particles is contacted with a second aerosol stream comprising oppositely charged particles resulting into a  
25 combined aerosol stream to form the powder particle.

          Thus the present invention provides a method for the manufacture of powder particles, which together constitute a powder, which powder is comprised of less charged or substantially neutral particles. The method allows for, for example,  
30 the use of aerosol streams of different composition enabling physical and chemical reactions to occur, and for the coating of particles.

          The charged powders manufactured according to the state of the art tend to form agglomerates, making them less

suitable in the manufacture of high quality finished surfaces. The charged powders also tend to clog up pipelines, which interferes with both production of the powder and use thereof. Thus, the method according to the invention provides  
5 a powder having an improved industrial applicability while in addition a higher powder yield is obtained.

In the field of fuel injection it is known to study the phenomenon of mixing two aerosol fuel streams by contacting two similarly charged aerosol fuel streams. (Dunn P.F. et  
10 al. the mixing of electrically-charged droplets between and within electrohydrodynamic fine sprays, J. Aerosol Sci. vol. 25, 0.6, pp. 1213-1227, 1994).

It is also known to manufacture a homogeneous mixture by contacting charged granules with an oppositely  
15 charged powder (Thesis of P. Vercoulen; Electrostatic processing of particles. Technical University of Delft, the Netherlands). To this end a powder, comprising particles in the micron range, is sprayed and subsequently charged, for example using a corona discharge device, before being con-  
20 tacted with oppositely charged solid granules having diameters in the order of 2 mm. The particulate starting materials were manufactured using conventional techniques, i.e. grinding.

According to a preferred embodiment of the invention  
25 the amount of charge of the first aerosol stream and the amount of charge of the second aerosol stream are controlled to yield a substantially neutral powder.

Thus a higher yield of powder can be obtained than previously achievable.

30 According to a preferred embodiment the particles of at least the first aerosol stream comprising charged particles are generated by electrohydrodynamic spraying.

Electrohydrodynamic spraying allows for the generation of charged aerosol streams having well defined particle  
35 size distributions, wherein the liquid particles are charged at the instant the liquid particle is formed, i.e. the droplets do not have to be charged afterwards in a separate charging step.

According to a preferred embodiment the first aero-

sol stream comprises particles comprising a solvent and a solute, said solvent being evaporated to yield a substantially dry powder particle.

5 This allows for the manufacture of a powder mixture comprising charged particles having an identical composition but opposite charge, a powder mixture comprising charged particles having a different composition, when aerosol streams with different composition are used, and opposite charge. Another possibility is the manufacture of a powder  
10 comprising two or more attached subunits. This method is characterized in that a part of the solvent is evaporated from the first aerosol stream to form a first aerosol stream being composed of solid, sticky charged particles which is contacted with the second charged aerosol stream comprising  
15 solid charged particles resulting in the combined aerosol stream which is converted into an essentially dry powder. Thus it is possible to make aerosol particles with a specific shape, the subunits having the same or a different composition.

20 A particularly preferred embodiment of the method according to the invention is characterized in that, when contacted, both the first and the second aerosol stream comprise liquid charged particles.

25 This embodiment allows for a multitude of physical and chemical reactions to occur.

Advantageously the method according to the invention comprises, after contacting the first aerosol stream with the second aerosol stream, separation of particles with the desired composition according to their charge to mass ratio.

30 As the amount of charge is proportional to the mass of the particle (or, in case of a particle comprising an evaporating solvent, to the mass of the solute), the composition of the particle is reflected in the charge to mass ratio of the particle formed.

35 Yet another preferred method of manufacturing a powder according to the invention is characterized in that at least the first aerosol stream, being comprised of larger particles and satellite particles, is subjected to a particle separation step providing a substantially monodisperse aero-

sol stream whereafter the substantially monodisperse aerosol stream is contacted with the oppositely charged aerosol stream.

5 This embodiment, which is especially useful with electrohydrodynamic spraying, provides for a powder to be produced having a even narrower particle size distribution. Accordingly it is preferred that both the first and the second aerosol stream are subjected to the particle separation step.

10 According to an advantageous embodiment, the separation step is conducted using a grounded electrode. The grounded electrode, placed near or in that part of the aerosol stream where the particles to be removed pass and more distantly spaced from the desired particles, serves as a  
15 simple and effective means to attract and remove the unwanted particles. Thus an aerosol stream enriched in the desired particles is obtained and subsequently brought into contact with the oppositely charged aerosol stream.

The invention also relates to powder comprising  
20 ceramic precursor powder particles, polymer-comprising powder particles or powder particles comprising a pharmaceutical compound, for example coated powder particles, as well as a pharmaceutical composition comprising such a pharmaceutical compound-comprising powder together with a pharmaceutically  
25 acceptable carrier or diluent.

Moreover the invention relates to a method of manufacturing a ceramic product characterized in that a ceramic precursor powder according to the invention is sintered.

The method allows for the manufacture of very fine  
30 ceramic precursor powders without grinding as well as powders with compositions which until now could not be obtained or only with great difficulty. If the above mentioned separation step is performed, providing two aerosol streams comprised of satellite droplets, highly desired ceramic precursor  
35 nanoparticles can be obtained, suitable for defect free ceramic products.

Finally, the invention relates to an apparatus for working the method according to the invention, comprising an electrode having an inlet and an outlet, a channel connecting

the inlet and the outlet, the outlet being an orifice in the centre of an electrically conducting area opening into a chamber, wherein the electrically conducting area is defined by a barrier, said barrier preventing the flow of liquid beyond the electrically conducting area and the chamber having a counter electrode as well as an exhaust opening for a product formed by electro-hydrodynamic spraying.

The apparatus is characterized in that the chamber is a mixing chamber and the apparatus is provided with a second electrode having an orifice opening into the chamber.

The invention will be hereinafter explained in more detail with reference to the drawing, in which the only figure represents a schematic cross sectional view of an apparatus for working the method according to the invention.

The present invention provides a method for contacting a first charged aerosol stream comprised of charged particles with a second aerosol stream comprised of oppositely charged particles in a mixing zone resulting into a combined aerosol stream which is subsequently converted into a powder. Particles making up an aerosol stream have a diameter of 100  $\mu\text{m}$  or less - usually in the micron range.

Advantageously the first charged aerosol stream is generated using electrohydrodynamic spraying, which method is well known in the art. A liquid A is passed via a channel 1 through a narrow orifice 2, for example with a diameter of 0,2 mm, of a nozzle 3. A high voltage, typically 5 - 30 kV is supplied over the nozzle 3 and an annular grounded counter electrode 4. The high voltage accelerates the liquid A through channel 1 and towards the annular counter electrode 4. At the orifice 1 a liquid jet B emerges which breaks up into charged droplets forming a conical stream of droplets having narrow size, charge density and velocity distribution. Because of their initial speed the droplets do not encounter the counter electrode 4. During the breaking up process smaller droplets, known as satellite droplets, are created as well, resulting in a bi-modal particle size distribution. These satellite droplets, being very small, end up in the outer periphery of the conical aerosol stream.

If desired it is possible to eliminate one of both

types of droplets by suitably placing a grounded electrode 5 near its path, for example in position C for the removal of the satellite droplets or in position D for the removal of the larger droplets.

5           The charged aerosol stream comprised of charged droplets is contacted with an oppositely charged second aerosol stream in a mixing zone 6. This second aerosol stream may be comprised of liquid particles, i.e. droplets, or solid particles.

10           Due to the opposite charge of the particles of each aerosol stream, the particles of the different aerosol streams are attracted to each other and combine, forming less charged and even neutral particles.

          Advantageously the amount of charge of the first  
15 aerosol stream and the amount of charge of the second aerosol stream are controlled to yield a neutral powder. This can be achieved in several ways, two of which are discussed. First-ly, the amount of charge per second of the first aerosol stream should be equal to the amount of charge per second of  
20 the second aerosol stream. Secondly, if one of the streams consists of very many fine particles in comparison to the particles of the other stream, many fine particles will be needed to neutralize a large particle, allowing accurate neutralization of the large particle. Thus it may be possible  
25 to increase the yield of neutral particles. An aerosol stream comprising very small particles may be obtained exploiting the Rayleigh break-up phenomenon, which occurs when the charge density in a particle becomes too high, due to evaporation of a solvent. The very fine particles may be used in  
30 excess, the surplus being wasted. To waste the surplus, a charged electrode may be used and advantageously the very fine particles consist of a volatile solvent only.

          Mixing of the aerosol streams can be enhanced by supplying a gas G, usually an inert gas, to the mixing zone 6  
35 where the first and the second aerosol stream are contacted. The gas flow also provides a convenient way to carry off the powder formed. The gas G may be supplied through inlets 9 and prevents space charge accumulation in front of the nozzles 3, which would result in an increase in electrical field inten-



sity and unstable aerosol streams.

The method according to the invention results in a powder comprised of less charged or substantially neutral particles. Charged product particles may be removed using a grounded electrode yielding a product stream of substantially neutral particles, or classified according to their charge to mass ratio using charged electrodes 10a, 10b. Such a separation may be very valuable, for example to select particles with a desired composition. The manufacture of powders of various composition will be discussed below.

As stated earlier, the second aerosol stream may be comprised of liquid particles, i.e. droplets, or solid particles. If the second aerosol stream is comprised of solid particles these may have been charged tribologically or by using for example a corona discharge device. However, preferably the second aerosol stream is generated (both for solid and liquid particles) using electrohydrodynamic spraying as well, as shown in the figure, wherein parts indicated with reference numerals with an apostrophe correspond to those mentioned above having the same number. Using a solute-containing liquid, evaporation of the solvent before contacting the stream results in charged solid particles quickly and efficiently.

If the first aerosol stream is composed of liquid particles while contacting the second aerosol stream, it is possible to manufacture coated particles. Coated particles are for example of interest in the manufacture of pharmaceutical compositions, for example for the quick, delayed or sustained release of a pharmaceutically active compound. When it is desired to coat a liquid particle, it may be necessary to incorporate a surfactant.

Contacting the first charged aerosol stream with a second charged aerosol stream of liquid particles opens a whole range of possibilities to manufacture particles with various composition.

According to a preferred embodiment the liquid of the first aerosol stream comprises a first agent and the liquid of the second aerosol stream comprises a second agent. Thus it is possible to perform many physical and chemical

reactions in very tiny droplets.

For example, if the liquids of the first and the second aerosol stream are miscible, homogeneous physical or chemical processes may occur in each newly formed droplet. If the liquids are immiscible heterogeneous processes may occur. Typical physical processes include precipitation and crystallization processes. Thus the method according to the invention may, for example, result in particles each comprising an amorphous mixture of compounds which were originally present in each of the aerosol streams, or a crystal. In this way it is for example possible to manufacture ceramic precursor powders. Amongst the ceramic precursor powders those for the manufacture of high temperature superconductors can be mentioned.

A potentially useful embodiment comprises contacting a water miscible organic solvent comprising a not or sparingly water soluble polymer with an oppositely charged aqueous aerosol stream, the water causing the polymer to precipitate. Another simple way to obtain a precipitate is by using an alkaline and acid liquid for the respective aerosol streams, if the solubility of the solute is pH dependent.

A preferred embodiment of the method according to the invention is characterized in that the liquid of the first aerosol stream comprises a first reagent and the liquid of the second aerosol stream comprises a second reagent and the reaction comprises a chemical reaction. In the present application the term "reagent" includes chemical or biological catalysts, for example an enzyme.

Due to chemical reactions the product particle may contain a new compound. The chemical reaction may be virtually any chemical reaction, for example a polymerisation reaction.

In case of a heterogeneous reaction, the invention allows for the preparation of compounds which can not be obtained efficiently by mixing the liquids in bulk, for example due to the formation of a solid reaction product preventing the remaining reagents from reacting.

The invention also relates to an electrode, suitable for use with the method according to the invention employing

electrohydrodynamic spraying, having an inlet and an outlet,  
a channel connecting the inlet and the outlet, the outlet  
being an orifice in the centre of an electrically conducting  
area 7, wherein the electrically conducting area 7 is defined  
5 by a barrier, said barrier preventing the flow of liquid  
outside the electrically conducting area 7.

According to the invention the electrode is charac-  
terized in that the electrically conducting area 7 is sur-  
rounded by a second area 8 of electrically conducting  
10 material, extending outwardly over at least 1 mm in radial  
direction from said barrier, preferably over a distance of at  
least half of the radius of the first area.

Thus a more homogenous electric field is generated,  
with a reduced radial component of the electrical field, near  
15 the nozzle 3. This is very important to avoid electrical dis-  
charges which would result in disturbed mixing of the first  
and second aerosol stream. The use of said electrode improves  
the size, charge density and velocity distribution of an  
aerosol stream generated using said electrode. In addition  
20 the electrode allows for the use of liquids with higher  
conductivities than with electrodes according to the state of  
the art.

The barrier may be, as shown in the figure, a steep  
recess, the wall thereof being for example at an angle of 90°  
25 with the first area. Preferably the first and second area lie  
in the same plane. Advantageously they are electrically  
connected.

It should be clear from the above, that the method  
according to the invention can be used to manufacture a  
30 powder comprising a mixture of physically separated charged  
particles having identical or different composition, a powder  
consisting of less charged or substantially neutral particles  
wherein each particle contains each of the compounds used, or  
a powder consisting of particles comprising a compound not  
35 present in the starting materials.

The present invention allows for the manufacture of  
powders which were previously only obtainable using emulsion  
techniques, which require the evaporation/removal of the  
solvent, making the techniques cumbersome and expensive.

The invention may also be used to control the size, structure and shape of the particles that make up the powder. By controlling the rate of evaporation of a solvent used, the person skilled in the art can achieve powders of, for  
5 example, porous, hollow or massive particles. Porous or amorphous particles may find application as catalysts. For coated particles, the thickness of coatings can be controlled by suitable choice of the solute concentration and droplet size. The rate of evaporation can be controlled by a suitable  
10 choice of solvent, heating (micro-wave, gas supplied at a particular temperature), suitable choice of the aerosol streams etc., as is well known by the person skilled in the art.

It will be appreciated that the present invention,  
15 as claimed in the appended claims, can be worked in several ways, as will be obvious for the person skilled in the art. For example, if mention is made of a liquid, the liquid may also comprise a molten solid. It is possible to improve the size distribution of an aerosol stream by, for example,  
20 superposing a high frequency alternating voltage on top of the constant voltage.

Rayleigh-break up may be used to generate droplets even smaller than satellite droplets and thus allow for the manufacture of extremely fine powders. Preferably a separation step is carried out before the aerosol stream generated  
25 is contacted with the second aerosol stream, as described above.

Apart from those already mentioned, the powders according to the invention will have many other uses, for  
30 example for calibration purposes and as seed material.

For scaling up the method according to the invention, an array of nozzles can be used, for example rows of nozzles with alternating a row for positively charged aerosol streams and a row for negatively charged aerosol streams.  
35 Advantageously, the nozzles are supplied with liquid from one supply, or in case of different liquids from two supplies only, and likewise the voltage can be supplied using one power supply for each polarity only.

The apparatus according to the invention may be pro-

vided with a moving counter electrode and/or electrode for  
the removal of charged particles, for example realised as a  
conveyor belt. Any particles adhering to the electrode are  
removed outside the mixing zone, for example outside the  
5 chamber, and are - depending on the type of powder formed -  
reused or disposed of.

CLAIMS

1. Method of manufacturing a dry powder particle by generating a charged aerosol stream comprised of charged initially liquid particles and converting said stream into powder particles, characterized in that the charged aerosol stream comprised of charged particles is contacted with a second aerosol stream comprising oppositely charged particles resulting into a combined aerosol stream to form the powder particle.

2. Method of manufacturing a powder particle according to claim 1, characterized in that the amount of charge of the first aerosol stream and the amount of charge of the second aerosol stream are controlled to yield a substantially neutral powder particle.

3. Method of manufacturing a powder particle according to claim 1 or 2, characterized in that the particles of at least the first aerosol stream comprising charged particles are generated by electro-hydrodynamic spraying.

4. Method of manufacturing a powder particle according to any of the preceding claims, characterized that the first aerosol stream is comprised of liquid particles comprising a solvent and a solute, said solvent being evaporated to yield a substantially dry powder particle.

5. Method of manufacturing a powder particle according to claim 4, characterized in that the first aerosol stream and second aerosol stream are contacted before the solvent is evaporated.

6. Method of manufacturing a powder particle according to any of the preceding claims, characterized in that, when contacted, both the first and the second aerosol stream comprise liquid charged particles.

7. Method of manufacturing a powder particle according to claim 6, characterized in that the first aerosol stream is generated using a liquid which is miscible with the liquid used to generate the second aerosol stream, allowing a homogeneous reaction to occur after contact.

8. Method of manufacturing a powder particle according to claim 6, characterized in that the first aerosol

stream is generated using a liquid which is immiscible with the liquid used to generate the second aerosol stream, allowing a heterogeneous reaction to occur after contact.

5 9. Method of manufacturing a powder particle according to claim 7 or 8, characterized in that the liquid of the first aerosol stream comprises a first reagent and the liquid of the second aerosol stream comprises a second reagent and the reaction comprises a chemical reaction.

10 10. Method of manufacturing a powder particle according to any of the preceding claims, characterized in that at least the first aerosol stream, being comprised of larger particles and satellite particles, is subjected to a particle separation step providing a substantially monodisperse aerosol stream whereafter the substantially monodisperse aerosol stream is contacted with the oppositely charged aerosol stream.

20 11. Method of manufacturing a powder particle according to claim 10, characterized in that both the first and the second aerosol stream are subjected to the particle separation step.

12. Method of manufacturing a powder particle according to claim 10 or 11, characterized in that the separation step is conducted using a grounded electrode.

25 13. Method of manufacturing a powder particle according to claim 5, characterized in that the solvent is evaporated from the first aerosol stream to form a first aerosol stream being composed of solid, sticky charged particles which is contacted with the second charged aerosol stream comprising solid charged particles resulting in the combined aerosol stream which is converted into an essentially dry powder.

35 14. Method of manufacturing a powder particle according to any of the preceding claims, characterized in that, after contacting the first aerosol stream with the second aerosol stream, particles with the desired composition are separated according to their charge to mass ratio.

15. Method of manufacturing a powder particle according to any of the preceding claims, characterized in that substantially neutral particles are separated from

substantially charged particles.

16. Powder manufactured according to any of the claims 1 - 15, characterized in that the powder comprises ceramic precursor powder particles.

5 17. Powder manufactured according to any of the claims 1 - 15, characterized in that the powder comprises polymer-comprising powder particles.

10 18. Powder manufactured according to any of the claims 1 - 15, characterized in that the powder comprises powder particles comprising a pharmaceutical compound.

19. Powder manufactured according to any of the claims 8, characterized in that the pharmaceutical compound-comprising powder is a coated powder.

15 20. Powder manufactured according to any of the claims 1 - 15, characterized in that the powder comprises catalyst-comprising powder particles.

21. Method of manufacturing a ceramic product, characterized in that the ceramic precursor powder according to claim 16 is sintered.

20 22. Pharmaceutical composition comprising a powder comprising at least one pharmaceutically active compound, characterized in that the powder is a powder according to claims 18 or 19, together with a pharmaceutically acceptable carrier or diluent.

25 23. Electrode, suitable for use in any of the claims 3 to 15, having an inlet and an outlet, a channel connecting the inlet and the outlet, the outlet being an orifice in the centre of an electrically conducting area, wherein the electrically conducting area is defined by a barrier, said barrier preventing the flow of liquid outside the electrically conducting area, characterized in that the electrically conducting area is surrounded by a second area of electrical-  
30 ly conducting material, extending outwardly over at least 1 mm in radial direction from said barrier.

35 24. Electrode according to claim 23, characterized in that the second area extends over a distance of at least half of the radius of the first area.

25. Apparatus for working the method according to any of the claims 1 to 15, comprising an electrode having an



inlet and an outlet, a channel connecting the inlet and the outlet, the outlet being an orifice in the centre of an electrically conducting area opening into a chamber, wherein the electrically conducting area is defined by a barrier, said barrier preventing the flow of liquid beyond the electrically conducting area and the chamber having a counter electrode as well as an exhaust opening for a product formed by electro-hydrodynamic spraying, characterized in that the chamber is a mixing chamber and the apparatus is provided with a second electrode having an orifice opening in the chamber.




Fig.

PCT/NL 97/00366

A. CLASSIFICATION OF SUBJECT MATTER		
IPC 6	B01J2/02	B01J2/00 B05B5/08 B01J14/00 B01J19/08
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC 6 B01J B05B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 1 360 193 A (SOCIETE ANONYME DE MACHINES ELECTROSTATIQUES (SAMES)) 12 August 1964	1-3,6, 12,15, 23-25
Y	see page 3, left-hand column, paragraph 5 - right-hand column, paragraph 3; figure 4	1,7
Y	DE 31 26 854 A (NUKEM GMBH) 27 January 1983	1,7
A	see page 4 see page 8, line 1 - page 10, paragraph 1; examples	9,17,18, 21,22
X	US 2 685 537 A (RUSSELL PAUL DUNMIRE) 3 August 1954 see the whole document	1,3,5, 18,19
X	US 4 383 767 A (MORIO JIDO) 17 May 1983 see figure 1	1,3,6,23
<input type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "Z" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
8 October 1997		15. 10. 97
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer  Van Belleghem, W

information on patent family members

PCT/NL 97/00366

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 1360193 A	12-08-64	NONE	
DE 3126854 A	27-01-83	NONE	
US 2685537 A	03-08-54	NONE	
US 4383767 A	17-05-83	JP 1130106 C	17-01-83
		JP 56065627 A	03-06-81
		JP 57028289 B	16-06-82

Form PCT/ISA/210 (patent family annex) (July 1992)